

GUNS

Tested: 17/04/2008 11:48

Number of Samples= 25

CLIENT: GUNALLO

Ref: YOUNG SHED RAMS

TAG	GREASY WT Kg	GWT % INDEX	MICRON u	MIC DEV	C.V.	S.D.	%>30u	CURVATURE (deg/mm)	SPINNING FINENESS
Flock									
Avg >			18.4		16.2	3.0	0.6	96	17.2
003			19.1	0.7	15.2	2.9	0.5	92	17.8
013			19.6	1.2	16.9	3.3	0.6	97	18.4
045			17.1	-1.2	15.2	2.6	0.2	108	15.9
131			19.4	1.0	15.5	3.0	0.5	102	18.1
223			19.7	1.4	14.2	2.8	0.8	91	18.2
224			20.2	1.8	16.8	3.4	0.7	84	19.0
237			18.4	0.1	15.2	2.8	0.4	90	17.1
264			17.4	-1.0	13.8	2.4	0.1	95	16.0
297			20.1	1.7	16.4	3.3	1.1	84	18.8
298			18.2	-0.2	17.6	3.2	0.7	91	17.2
305			18.5	0.2	15.1	2.8	0.3	94	17.2
320			18.8	0.5	17.0	3.2	0.7	107	17.7
326			16.4	-2.0	18.9	3.1	0.3	100	15.7
327			19.0	0.7	21.1	4.1	1.7	100	18.6
336			17.3	-1.0	18.5	3.2	0.6	101	16.5
P 280			16.4	-1.9	15.2	2.5	0.3	92	15.3
P 445			17.5	-0.9	16.0	2.8	0.3	102	16.3
P 521			18.3	0.0	12.6	2.3	0.2	103	16.8
P 530			17.8	-0.5	14.6	2.6	0.4	91	16.5
P 556			18.3	-0.1	17.5	3.2	0.8	103	17.3
P 563			20.8	2.4	18.3	3.8	1.0	82	19.8
P 652			17.5	-0.9	15.4	2.7	0.2	100	16.3
P 680			17.9	-0.4	15.1	2.7	0.6	103	16.7
P 836			18.6	0.3	17.7	3.3	0.8	90	17.7
P 880			17.3	-1.0	16.2	2.8	0.2	93	16.2